




























	Standard	Result	Product	Size (mm)
	EN ISO 24342	See separate table	REN113	914,4 X 101,6
	EN ISO 24346	2,5 mm	SP212	609,6 X 457,2
	EN ISO 24340	0,55 mm	SP213	609,6 X 457,2
		K-Guard+ PU coating	SP214	609,6 X 457,2
	Light industrial	10 years *	SP215	609,6 X 457,2
	Commercial	12 years *	SP216	609,6 X 457,2
	Residential	30 years *	SP217	609,6 X 457,2
		Micro	SP218	609,6 X 457,2
	EN ISO 23997	4398 g/m <sup>2</sup>	SP711	914,4 X 457,2
	EN 649/EN ISO 10582	Heterogeneous PVC	SP713	914,4 X 457,2
	EN 685/EN ISO 10874-Light industrial	42: Light industrial general	SP714	914,4 X 457,2
	EN 685/EN ISO 10874- Commercial	33: Commercial heavy	SP716	914,4 X 457,2
	EN 685/EN ISO 10874- Domestic	23: Domestic heavy	WP311	914,4 X 152,4
	EN 13501-1	B <sub>f1</sub> -s1	WP312	914,4 X 152,4
	EN ISO 26987/EN 423	Excellent	WP313	914,4 X 152,4
	EN ISO 105-B02	≥6	WP316	914,4 X 152,4
	EN 649	Group T	WP318	914,4 X 152,4
	EN ISO 10582	Type 1	WP321	914,4 X 152,4
	EN ISO 24344	Pass	WP322	914,4 X 152,4
	EN 434/EN ISO 23999	≤ 0,25%	WP327	914,4 X 152,4
	EN ISO 717-2/EN ISO 140-8	ΔL <sub>w</sub> = 2 dB	WP329	914,4 X 152,4
	EN 1815	Pass	WP330	914,4 X 152,4
	EN ISO 24343-1	Pass ≤ 0,1 mm	WP411	1219,2 X 228,6
	EN 425/ISO4918	Pass	WP412	1219,2 X 228,6
	ISO 8302	0,0097 m <sup>2</sup> K/W	WP413	1219,2 X 228,6
		Suitable for underfloor heating. Max 27 °C	WP414	1219,2 X 228,6
	DIN 51130	R10	WP415	1219,2 X 228,6
	EN 13893	DS	WP416	1219,2 X 228,6
	Universal	Yes	WP417	1219,2 X 228,6
	Acrylic	Yes	WP418	1219,2 X 228,6
	Epoxy	Yes	WP419	1219,2 X 228,6
	High Temperature	Yes	WP420	1219,2 X 228,6
	Pressure sensitive	Yes	WP421	1219,2 X 228,6
		Suitable	WP422	1219,2 X 228,6
	French VOC regulation (ISO 16000)	A+	WP423	1219,2 X 228,6
	DIBt/AgBB	Pass		
	QB 30	U3P3E2C2		
		n°788/354-001.1 For products supplied into France only		
		Yes		

\*Subject to terms see website

\*\*Certified by SATRA

\*\*\*Slip resistance is measured on freestanding ex-factory product. Slip resistance can be affected by many factors including but not limited to: product installation and underlayment, surface contamination, use, wear and how the product is maintained. Textural variation along the surface of the product can affect nominal values.

For more information:

Designflooring - T: +44 (0)1386 820105 | F: +44 (0)1386 820132

Designflooring SAS - T: 01 57 32 39 13 | F: 01 57 32 39 14

Designflooring GmbH - T: 0211 469 59203 | F: 0211 469 59204

Designflooring Nederland - T: 020 200 8282 | F: 020 200 8386

e: info@designflooring.com

[www.designflooring.com](http://www.designflooring.com)

 EPD®  
THE INTERNATIONAL EPD® SYSTEM