

	Standard	Result	Product	Size (mm)
	EN ISO 24342	See separate table	LLP92	1050,0 X 250,0
	EN ISO 24346	4,5 mm	LLP95	1050,0 X 250,0
	EN ISO 24340	0,55 mm	LLP99	1050,0 X 250,0
		K-Guard+ PU coating	LLP101	1050,0 X 250,0
	Light industrial	15 years	LLP102	1050,0 X 250,0
	Commercial	15 years	LLP106	1050,0 X 250,0
	Residential	30 years	LLP108	1050,0 X 250,0
		No	LLP109	1050,0 X 250,0
	EN ISO 23997	7470 g/m <sup>2</sup>	LLP112	1050,0 X 250,0
	EN 649/EN ISO 10582	Heterogeneous PVC	LLP113	1050,0 X 250,0
	EN 685/EN ISO 10874 - Light industrial	42: Light industrial general	LLP142	1050,0 X 250,0
	EN 685/EN ISO 10874 - Commercial	33: Commercial heavy	LLP143	1050,0 X 250,0
	EN 685/EN ISO 10874 - Domestic	23: Domestic heavy	LLP144	1050,0 X 250,0
	EN 13501-1	B <sub>fl</sub> -s1	LLP145	1050,0 X 250,0
	EN ISO 26987/EN 423	Excellent	LLP146	1050,0 X 250,0
	EN ISO 105-B02	≥7	LLP147	1050,0 X 250,0
	EN 649	Group T	LLP148	1050,0 X 250,0
	EN ISO 10582	Type 1	LLP149	1050,0 X 250,0
	EN ISO 24344	Pass	LLP150	1050,0 X 250,0
	EN 434/EN ISO 23999	≤ 0,10%	LLP151	1050,0 X 250,0
	EN ISO 717-2/EN ISO 140-8	ΔL <sub>w</sub> = 13 dB	LLT200	610,0 X 500,0
	EN 433/EN ISO 24343-1	Pass ≤ 0,1 mm	LLT201	610,0 X 500,0
	EN 425/ISO 4918	Pass	LLT202	610,0 X 500,0
	ISO 8302	0,0245 m <sup>2</sup> K/W	LLT203	610,0 X 500,0
		Suitable for underfloor heating. Max 27°C	LLT208	610,0 X 500,0
	DIN 51130	R10	LLT209	610,0 X 500,0
	EN 13893	DS	LLT210	610,0 X 500,0
		Most applications will not require the use of adhesives. However, we recommend the use of a tackifier for heavy traffic areas.	LLT211	610,0 X 500,0
			LLT214	610,0 X 500,0
			LLT215	610,0 X 500,0
		Suitable	LLT216	610,0 X 500,0
	French VOC regulation (ISO 16000)	A+	LLT217	610,0 X 500,0
		Yes	LLT218	610,0 X 500,0
			LLT219	610,0 X 500,0

\*Subject to terms see website

\*\*Slip resistance is measured on freestanding ex-factory product. Slip resistance can be affected by many factors, including but not limited to; product installation and underlayment, surface contamination, use, wear and how the product is maintained. Textural variation along the surface of the product can affect nominal values.

Designflooring - T: +44 (0)1386 820105 | F: +44 (0)1386 820132

Designflooring SAS - T: 01 57 32 39 13 | F: 01 57 32 39 14

Designflooring GmbH - T: 0211 469 59203 | F: 0211 469 59204

Designflooring Nederland - T: 020 200 8282 | F: 020 200 8386

e: [info@designflooring.com](mailto:info@designflooring.com)

[www.designflooring.com](http://www.designflooring.com)



EN 14041: 2004 (DOP 2017/LL/EN/02)  
 Notified body 0493  
 Floor coverings (internal)  
 ISO 10874 Class 23/33/42  
 Manufactured to ISO 10582



THE INTERNATIONAL EPD® SYSTEM